

# **TECHNICAL DATA SHEET**

## **KEXCELLED PAHT K7CFLM**

Product code: Revision Number: Revision date: TDS No.:

PAHT K7CFLM 04 14/01/2022 KT04.20.4104

## **Characteristic:**

High strength|high heat resistance|lower shrinkage

### **IDENTFICATION OF THE MATERIAL**

Trade name PAHT K7CFLM

Chemical name Carbon fiber reinforced polyamide 12

Use 3D Printing
Origin KEXCELLED

#### **GUIDELINE FOR PRINT SETTINGS**

Nozzle temperature $270\sim290^{\circ}$ CBed temperature $70\sim100^{\circ}$ CBed modificationTape or glue

Active cooling fanOFFLayer height0.2mmShell thickness≥0.8mmPrint speed40-80mm/s

Settings are based on a 0.4mm nozzle.

MATERIAL PROPERTIES		Test Method
Melt temperature	<b>~220</b> ℃	ISO 11357
Melt flow rate (MFR) 1	8~15g/10min	ISO 1133
Heat deflection temperature(HDT) <sup>2</sup>	<b>120</b> ℃	ISO 75
Vicat softening temperature(VST) <sup>3</sup>	<b>210</b> ℃	ISO 306
density	1.15g/cm <sup>3</sup>	ISO 1183
Odor	Odorless	1
Solubility	Insoluble in water	1

1.test conditions: T= 270 $^{\circ}$ C; m= 2.16kg. 2. test conditions:0.45MPa;120 $^{\circ}$ C/h. 3. test conditions:10N; 120 $^{\circ}$ C/h.



## MECHANICAL PROPERTIES|TENSILE TEST

Test Method ISO 527

All test specimens were printed using an

FlashForge Guider 2s under the

following conditions:

Print speed: 50mm/s Shell thickness: 1.2mm

Infill under 45°

	$\overline{}$

	Printed horizontal X,Y-axis	
Infill	100%	
Tensile strength (Mpa)	80~90	
Elongation at break (%)	2~4	
Emodulus (Mpa)	9000~10000	

### MECHANICAL PROPERTIES|IMPACT TEST Test Method ISO 179

The same conditions as tensile test.

1→impact direction




Infill	100%
Impact strength(KJ/m²)	20~25
Notch impact strength <sup>1</sup> (KJ/m <sup>2</sup> )	4~6

## MECHANICAL PROPERTIES | FLEXURAL TEST Test Method ISO 178

The same conditions as tensile test.

1→bending direction



Infill	100%	
Maximum force (Mpa)	120~130	
Flexural modulus (Mpa)	6000~8000	

<sup>1.</sup> notch type: type A

<sup>\*</sup>The mechanical properties of nylon and Its HDT have a great relationship with its water absorption rate. This table shows its performance in its dry state.



FILAMENT SPECIFICATION		Test Method
Diameter 1.75mm	1.75±0.03mm	EX1125
Diameter 2.85mm	2.85±0.03mm	EX1125
Max roundness deviation (1.75)	0.03mm	EX1125
Max roundness deviation (2.85)	0.03mm	EX1125
Net weight on reel	1kg	EX1125