

## TECHNICAL DATA SHEET

### KEXCELLED PETG K5

<b>Product code:</b>	<b>Revision Number:</b>	<b>Revision date:</b>	<b>TDS No.:</b>
PETG K5	03	14/01/2022	KT04.20.2101

---

### BRIEF INTRODUCTION

Filament suitable for all commercially available leading brands FDM/FFF Printers.

#### Characteristic:

environmentally friendly|excellent effect applied to 3D printing|good interlayer bond|no buckling deformation| excellent toughness.

### IDENTIFICATION OF THE MATERIAL

<b>Trade name</b>	PETG K5
<b>Chemical name</b>	Poly(ethylene terephthalate-co-1,4-cyclohexylenedimethylene terephthalate)
<b>Use</b>	3D Printing
<b>Origin</b>	KEXCELLED

### GUIDELINE FOR PRINT SETTINGS

<b>Nozzle temperature</b>	225~245°C
<b>Bed temperature</b>	70~80°C
<b>Bed modification</b>	NO
<b>Active cooling fan</b>	0~50%
<b>Layer height</b>	0.2mm
<b>Shell thickness</b>	≥0.8mm
<b>Print speed</b>	40-80mm/s

Settings are based on a 0.4mm nozzle.

<b>MATERIAL PROPERTIES</b>		<b>Test Method</b>
<b>Melt temperature</b>	~200°C	ISO 11357
<b>Glass transition temperature</b>	~70°C	ISO 11357
<b>Melt flow rate (MFR) <sup>1</sup></b>	8~12g/10min	/
<b>Heat deflection temperature(HDT)<sup>2</sup></b>	70°C	ISO 75
<b>Vicat softening temperature(VST)<sup>3</sup></b>	80°C	ISO 306
<b>density</b>	1.27g/cm <sup>3</sup>	ISO 1183
<b>Odor</b>	Odorless	/
<b>Solubility</b>	Insoluble in water	/

1.test conditions: T= 230°C; m= 2.16kg.

2. test conditions:0.45MPa;120°C/h.

3. test conditions:10N; 120°C/h.

**MECHANICAL PROPERTIES|TENSILE TEST**
**Test Method ISO 527**

All test specimens were printed using an FlashForge Guider 2s under the following conditions:

Printing temperature: 225°C

Heated bed temperature: 75°C

Print speed: 50mm/s

Shell thickness: 1.2mm

Infill under 45°




Printed horizontal X,Y-axis

Infill	100%
Tensile strength (Mpa)	40~45
Elongation at break (%)	8~10
Emodulus (Mpa)	3200~3600

**MECHANICAL PROPERTIES|IMPACT TEST**
**Test Method ISO 179**

The same conditions as tensile test.

1→impact direction




Infill	100%
Impact strength (KJ/m <sup>2</sup> )	60~90
Notch impact strength <sup>1</sup> (KJ/m <sup>2</sup> )	4~6

**MECHANICAL PROPERTIES |FLEXURAL TEST**
**Test Method ISO 178**

The same conditions as tensile test.

1→bending direction



Infill	100%
Maximum force (Mpa)	65~70
Flexural modulus (Mpa)	1700~1900

1. notch type: type A

FILAMENT SPECIFICATION		Test Method
Diameter 1.75mm	1.75±0.03mm	EX1125
Diameter 2.85mm	2.85±0.03mm	EX1125
Diameter 3.00mm	3.00±0.03mm	EX1125
Max roundness deviation (1.75)	0.03mm	EX1125
Max roundness deviation (2.85)	0.03mm	EX1125
Max roundness deviation (3.00)	0.03mm	EX1125
Net weight on reel	1kg	EX1125