

## TECHNICAL DATA SHEET

### KEXCELLED PLA K5

|                      |                         |                       |                 |
|----------------------|-------------------------|-----------------------|-----------------|
| <b>Product code:</b> | <b>Revision Number:</b> | <b>Revision date:</b> | <b>TDS No.:</b> |
| PLA K5               | 04                      | 11/01/2022            | KT04.20.1001    |

#### Characteristic:

Environmentally friendly | good interlayer bond | no buckling deformation | high melt flow rate.

#### IDENTIFICATION OF THE MATERIAL

|                      |                 |
|----------------------|-----------------|
| <b>Trade name</b>    | PLA K5          |
| <b>Chemical name</b> | Polylactic Acid |
| <b>Use</b>           | 3D Printing     |
| <b>Origin</b>        | KEXCELLED       |

#### GUIDELINE FOR PRINT SETTINGS

|                           |                         |
|---------------------------|-------------------------|
| <b>Nozzle temperature</b> | 190~220°C               |
| <b>Bed temperature</b>    | 30~60°C                 |
| <b>Bed modification</b>   | Tape or glue below 60°C |
| <b>Active cooling fan</b> | ON, 50%~100%            |
| <b>Layer height</b>       | 0.2mm                   |
| <b>Shell thickness</b>    | ≥0.8mm                  |
| <b>Print speed</b>        | 40-100mm/s              |

Settings are based on a 0.4mm nozzle.

#### MATERIAL PROPERTIES

|   |                            | Test Method |
|---|----------------------------|-------------|
| <b>Melt temperature</b>                             | ~160°C                     | ISO 11357   |
| <b>Glass transition temperature</b>                 | ~60°C                      | ISO 11357   |
| <b>Melt flow rate (MFR)<sup>1</sup></b>             | 6~12 g/10min               | ISO 1133    |
| <b>Heat deflection temperature(HDT)<sup>2</sup></b> | 57°C                       | ISO 75      |
| <b>Vicat softening temperature(VST)<sup>3</sup></b> | 57°C                       | ISO 306     |
| <b>Density</b>                                      | 1.23~1.25g/cm <sup>3</sup> | ISO 1183    |
| <b>Odor</b>   | Odorless                   | /           |
| <b>Solubility</b>                                   | Insoluble in water         | /           |

1. test conditions: T= 190°C; m= 2.16kg.

2. test conditions: 0.45MPa; 120°C/h.

3. test conditions: 10N; 120°C/h.

**MECHANICAL PROPERTIES|TENSILE TEST**
**Test Method ISO 527**

All test specimens were printed using an FlashForge Guider 2s under the following conditions:

Printing temperature: 210°C

Heated bed temperature: 60°C

Print speed: 50mm/s

Shell thickness: 1.2mm

Infill under 45°




Printed horizontal X,Y-axis

|                         |           |
|-------------------------|-----------|
| Infill                  | 100%      |
| Tensile strength (Mpa)  | 36~42     |
| Elongation at break (%) | 10~15     |
| E modulus (Mpa)         | 4500~4800 |

**MECHANICAL PROPERTIES|IMPACT TEST**
**Test Method ISO 179**

The same conditions as tensile test.

1→impact direction




|   |       |
|---|-------|
| Infill  | 100%  |
| Impact strength (KJ/m <sup>2</sup> )                    | 25~30 |
| Notch impact strength <sup>1</sup> (KJ/m <sup>2</sup> ) | 4~8   |

**MECHANICAL PROPERTIES |FLEXURAL TEST**
**Test Method ISO 178**

The same conditions as tensile test.

1→bending direction



|                        |           |
|------------------------|-----------|
| Infill                 | 100%      |
| Maximum force (Mpa)    | 70~75     |
| Flexural modulus (Mpa) | 2700~3000 |

1. notch type: type A

| FILAMENT SPECIFICATION         |             | Test Method |
|--------------------------------|-------------|-------------|
| Diameter 1.75mm                | 1.75±0.03mm | EX1125      |
| Diameter 2.85mm                | 2.85±0.03mm | EX1125      |
| Diameter 3.00mm                | 3.00±0.03mm | EX1125      |
| Max roundness deviation (1.75) | 0.03mm      | EX1125      |
| Max roundness deviation (2.85) | 0.03mm      | EX1125      |
| Max roundness deviation (3.00) | 0.03mm      | EX1125      |
| Net weight on reel             | 1kg         | EX1125      |