

TECHNICAL DATA SHEET

KEXCELLED PLA K5C

Product code:	Revision Number:	Revision date:	TDS No.:
PLA K5C	01	011/01/2022	KT04.20.1004

BRIEF INTRODUCTION

Filament suitable for all commercially available leading brands FDM/FFF Printers.

Characteristic:

Environmentally friendly|Excellent printing effect|good interlayer bond|no buckling deformation|Color varies with temperature

IDENTIFICATION OF THE MATERIAL

Trade name	PLA K5C
Chemical name	Polylactic Acid
Use	3D Printing
Origin	KEXCELLED

GUIDELINE FOR PRINT SETTINGS

Nozzle temperature	190~220°C
Bed temperature	30~60°C
Bed modification	Tape or glue below 60°C
Active cooling fan	ON, 50%~100%
Layer height	0.2mm
Shell thickness	≥0.8mm
Print speed	40-80mm/s

Settings are based on a 0.4mm nozzle.

MATERIAL PROPERTIES

		Test Method
Melt temperature	~160°C	ISO 11357
Glass transition temperature	~60°C	ISO 11357
Melt flow rate (MFR)¹	7~12g/10min	ISO 1133
Heat deflection temperature(HDT)²	55°C	ISO 75
Vicat softening temperature(VST)³	58°C	ISO 306
density	1.23g/cm ³	ISO 1183
Odor	Odorless	/
Solubility	Insoluble in water	/

1.test conditions: T= 190°C; m= 2.16kg.

2. test conditions:0.45MPa;120°C/h.
3. test conditions:10N; 120°C/h.

MECHANICAL PROPERTIES TENSILE TEST	Test Method ISO 527
---	----------------------------

All test specimens were printed using an FlashForge Guider 2s under the following conditions:

- Printing temperature: 210°C
- Heated bed temperature: 60°C
- Print speed: 50mm/s
- Shell thickness: 1.2mm
- Infill under 45°




Printed horizontal X,Y-axis

Infill	100%
Tensile strength (Mpa)	40~45
Elongation at break (%)	6~10
Emodulus (Mpa)	4200~4500

MECHANICAL PROPERTIES IMPACT TEST	Test Method ISO 179
--	----------------------------

The same conditions as tensile test.

1→impact direction




Charpy(ep)

Infill	100%
Impact strength (KJ/m ²)	18~22
Notch impact strength ¹ (KJ/m ²)	2~4

MECHANICAL PROPERTIES FLEXURAL TEST	Test Method ISO 178
---	----------------------------

The same conditions as tensile test.

1→bending direction



Normal

Infill	100%
Maximum force (Mpa)	85~95
Flexural modulus (Mpa)	3000~3500

1. notch type: type A

FILAMENT SPECIFICATION		Test Method
Diameter 1.75mm	1.75±0.03mm	EX1125
Diameter 2.85mm	2.85±0.03mm	EX1125
Diameter 3.00mm	3.00±0.03mm	EX1125
Max roundness deviation (1.75)	0.03mm	EX1125
Max roundness deviation (2.85)	0.03mm	EX1125
Max roundness deviation (3.00)	0.03mm	EX1125
Net weight on reel	1kg	EX1125